

Appl. No. 09/941,096
Amdt. Dated September 8, 2003
Reply to Office Action of June 9, 2003

Pending Claims:

This listing will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

Claim 1 (previously amended): A composite sheet comprising:

a substantially non-porous and moisture-pervious thermoplastic synthetic resin film having an upper and a lower surface;

a thermoplastic synthetic resin fibrous sheet bonded to at least one of the upper and lower surfaces of said thermoplastic synthetic resin film;

a plurality of bulgy structural zones formed on a surface of the thermoplastic synthetic resin film that is opposed to said thermoplastic synthetic resin fibrous sheet, the plurality of bulgy structural zones extending in one direction in parallel and spaced apart from one another; and

substantially flat zones defined between adjacent ones of the bulgy structural zones,

said thermoplastic synthetic resin film being welded along said bulgy structural zones to said thermoplastic synthetic resin fibrous sheet.

Claim 2 (previously amended): The composite sheet according to Claim 1, wherein said thermoplastic synthetic resin film comprises a thermoplastic elastomer resin.

Appl. No. 09/941,096
Amdt. Dated September 8, 2003
Reply to Office Action of June 9, 2003

Claim 3 (previously amended): The composite sheet according to Claim 2, wherein said thermoplastic elastomer resin is a member selected from the group consisting of urethane-based, ester-based and amide-based thermoplastic elastomer resins and said thermoplastic synthetic resin film is substantially non-porous and moisture-pervious.

Claim 4 (previously amended): The composite sheet according to Claim 1, wherein said thermoplastic synthetic resin fibrous sheet comprises a fibrous nonwoven fabric made of thermoplastic synthetic resin fibers.

Claim 5 (previously amended): The composite sheet according to Claim 4, wherein said fibrous nonwoven fabric comprises an elastically stretchable nonwoven fabric obtained by melt-spinning thermoplastic elastomer resin and said thermoplastic synthetic resin film is bonded along the bulgy structural zones to said elastically stretchable nonwoven fabric in an untensioned state.

Claim 6 (previously amended): The composite sheet according to Claim 11, wherein each of said bulgy structural zones has a width of from about 0.2 to about 2.0 mm and a maximum thickness of from about 40 to about 150 μm and each of said flat zones has a thickness of from about 5 to about 100 μm .

Appl. No. 09/941,096
Amdt. Dated September 8, 2003
Reply to Office Action of June 9, 2003

Claim 7 (previously amended): The composite sheet according to Claim 1, wherein said composite sheet has a water-resistance of 49 hpa or higher as measured in accordance with JIS 1092A.

Claim 8 (previously amended): The composite sheet according to Claim 1, wherein said composite sheet has a moisture-permeability of $3000 \text{ g/m}^2 \cdot 24 \text{ Hr}$ or higher as measured in accordance with JIS L 1099A.

Claim 9 (previously added): A composite sheet comprising:

- a thermoplastic synthetic resin fibrous sheet;

- a thermoplastic synthetic resin film bonded to the thermoplastic synthetic resin fibrous sheets to form a composite sheet having a substantially flat exposed surface defined by the thermoplastic synthetic resin film;

- a plurality of bulgy structural zones formed on a surface of the thermoplastic synthetic resin film that is opposed to said thermoplastic synthetic resin fibrous sheet, the plurality of bulgy structural zones extending in one direction in parallel and spaced apart from one another; and

- substantially flat zones defined between adjacent ones of the bulgy structural zones,

- said thermoplastic synthetic resin film being welded along said bulgy structural zones to said thermoplastic synthetic resin fibrous sheet.

Claim 10 (previously added): A composite sheet comprising:

Appl. No. 09/941,096
Amdt. Dated September 8, 2003
Reply to Office Action of June 9, 2003

an imperforated thermoplastic synthetic resin film having an upper and a lower surface;
a thermoplastic synthetic resin fibrous sheet bonded to at least one of the upper and lower surfaces of said thermoplastic synthetic resin film;
a plurality of bulgy structural zones formed on a surface of the thermoplastic synthetic resin film that is opposed to said thermoplastic synthetic resin fibrous sheet, the plurality of bulgy structural zones extending in one direction in parallel and spaced apart from one another; and
substantially flat zones defined between adjacent ones of the bulgy structural zones,
said thermoplastic synthetic resin film being welded along said bulgy structural zones to said thermoplastic synthetic resin fibrous sheet.